



ARPLANK 30 contains **25%** of PCR (post-consumer recycled) polyethylene.

Physical properties

	Test method	Typical result
Length (mm)	ISO 1923	≥ 1,800
Width (mm)	ISO 1923	≥ 1,200
Thickness (mm)	ISO 1923	≥ 150
Density (kg/m ³)	ISO 845	30
Compressive strength 25% strain (kPa) 50% strain (kPa)	ISO 7214	80 140
Tensile strength (kPa) Tensile elongation (%)	ISO 7214	400 50
Compression set Stabilising 30min (%) Stabilising 24h (%)	ISO 7214 25% - 22h loading	16 3
Compression set Stabilising 30min (%) Stabilising 24h (%)	ISO 7214 50% - 22h loading	39 5
Tear strength (N/cm)	ISO 8067-B	25
Hardness Shore 00	ISO 868	60
Water absorption (%)	DIN 53428	< 1
Thermal conductivity (W/(m.K)) Test temperature 10°C Test temperature 23°C	ISO 8301	0.039 0.040
Service temperature (°C)	Internal	100
Flammability	FMVSS302 (Burn rate <100mm/min)	Pass

Version 02

This information is provided as a convenience to customers and reflects the results of internal tests conducted on ARPLANK samples. While all reasonable care has been taken to ensure that this information is accurate as of the date of issue, JSP does not represent, warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information. ARPLANK is a registered trade mark.